

## Regranulate

### HDPE SOLLITEN

For above mentioned supply, the following values have been measured.

#### Technical data

Parameter	Value	Unit
Melt Flow Rate (190°C/5,00 kg)	1,492	g/10 min
Humidity	0,0577	%
Bulk weight	528,13	kg/m <sup>3</sup>
Ash content	1,423	%

\*the measured values relate to a specific batch and other batches may have slight differences in individual parameters.

**Use:** Extrusion

**Color:** Black

**Storage:** The material should be stored dry, free of direct sunlight, up to a maximum temperature of 50 °C.

**Packaging:** BigBag or octabin on palett

**Safety information:** refers to the primary material, for the regranulate before the product is used, customers and other users should have their own independent opinion that the product is suitable for the intended use.

