

Regranulate
HIPS SOLLISTYREN

For above mentioned supply, the following values have been measured.

Technical data

Parameter	Value	Unit
Melt Flow Rate (200°C/5,00 kg)	10,18	g/10 min
Humidity	0,07	%
Bulk weight	567,90	kg/m ³
Ash content	1,78	%
Density	1,04	g/cm ³
Charpy notched impact strength	7,70	kJ/m ²
Tensile modulus	1847	MPa
Yield stress	22,0	MPa
Yield strain	2,1	%

*the measured values relate to a specific batch and other batches may have slight differences in individual parameters.

Use: Injection moulding

Color: White

Storage: The material should be stored dry, free of direct sunlight, up to a maximum temperature of 50 °C.

Packaging: BigBag or octabin on palett

Safety information: refers to the primary material, for the regranulate before the product is used, customers and other users should have their own independent opinion that the product is suitable for the intended use.

SOLLAU CZ s.r.o.

Hřivínův Újezd 212 | 763 07 Velký Ořešov

IČ: 03401065 | DIČ: CZ03401065

Tel.: +420 576 013 873 | www.sollau-cz.com

