

Regranulate
PC/ABS SOLLABLEND T65

For above mentioned supply, the following values have been measured.

Technical data

Parameter	Value	Unit
Melt Flow Rate (260°C/5,0 kg)	20-30	g/10 min
Density	1,13	g/cm ³
Vicat Softening Temperature	125	°C
E-Modulus	> 2100	MPa
Tensile strength	> 40	MPa
Elongation at break	> 30	%
Surface resistivity	1E16	Ohm
Izod notched impact strength	> 250	J/m ²
Measured flammability rating 3,2 mm	HB	Class
Measured flammability rating 1,6 mm	HB	Class

*the measured values relate to a specific batch and other batches may have slight differences in individual parameters.

Use: Injection moulding

Color: black

Storage: The material should be stored dry, free of direct sunlight, up to a maximum temperature of 50 °C.

Packaging: BigBag or octabin on palett

Safety information: refers to the primary material, for the regranulate before the product is used, customers and other users should have their own independent opinion that the product is suitable for the intended use.

SOLLAU CZ s.r.o.

Hřivínův Újezd 212 | 763 07 Velký Ořešov

IČ: 03401065 | DIČ: CZ03401065

Tel.: +420 576 013 873 | www.sollau-cz.com

